

IN THE CLAIMS

Claims 1-62 (canceled)

63. (new) A method of treating the surface of a metallic workpiece comprising the steps of:

- a) providing a surface comprising at least one of a metal, on a metal alloy or a mixture thereof, whereby at least one of the metal or metal alloy is anodizable and is used as an electrode;
- b) contacting said metallic surface with an anodizing solution;
- c) providing at least one other electrode in contact with said anodizing solution; and
- d) passing an electric current between said metallic surface and said other electrode through said anodizing solution,
- e) wherein said anodizing solution is an aqueous solution having a pH greater than 7 and comprises:
 - i. a phosphorus and oxygen containing anion;
 - ii. at least one water-soluble inorganic hydroxide;
 - iii. at least one surfactant; and
 - iv. at least one alcohol having at least one alkaline radical group or at least one alkaline hydrolyzed silane or a mixture thereof.

- i. 64. (new) The method of claim 63, wherein the metal or metal alloy comprises magnesium, magnesium alloy, aluminum, aluminum alloy, titanium, titanium alloy, beryllium or beryllium alloy.

65. (new) The method of claim 63, wherein the phosphorous and oxygen containing anion is phosphate.

- i. 66. (new) The method of claim 65, wherein the metal or metal alloy comprises magnesium, magnesium alloy, aluminum, aluminum alloy, titanium, titanium alloy, beryllium or beryllium alloy, and the surface is contacted with the anodizing solution by immersion

67. (new) The method of claim 63, wherein said workpiece is used as an anode for direct current or as an electrode for alternative current.

68. (new) The method of claim 63, wherein the surface of the workpiece is treated with at least one cleaning solution or with at least one deoxidizer solution prior to contacting the surface with the anodizing solution.

69. (new) The method of claim 63, wherein at least one rinsing solution is applied to the surface prior to or after the application of the anodizing solution.

70. (new) The method of claim 63, wherein said current has a density of less than 4 A/dm² of said metallic surface.

71. (new) The method of claim 63, wherein during said passing an electric current, the anodizing solution is maintained at a temperature of between 0 °C and 60 °C.

72. (new) The method of claim 63, wherein the coating has an average coating thickness in the range from 2 to 50 µm.

73. (new) The method of claim 63, further comprising the step of applying at least one coating, wherein the coating is a coating comprising a solution containing at least one acid, an alkaline solution, a solution containing at least one silane, a paint, a dispersion or solution containing at least one resin, a powder paint or an electroless deposited metal like nickel rich coating.